

# Oven / Calendering



**This operation gives drying wires dimensional stability (length, width, thread count, porosity) and strengthens the needled fibres onto the base of wet section felts.**

## **Characteristics:**

Temperature: 180° C

Pressure: 3 bars

Calendering: 3 bars

Maximum canvas width: 9 metres

Maximum canvas length: 80 metres